



# Test Report

No. F690101/LF-CTSAYSA18-03726

Issued Date: 2018. 03. 12

Page 1 of 3

**MINSEO COATING FLEX CO.,LTD**  
382 Jeongmun-ro, Wollong-myeon,  
Paju-si, Gyeonggi-do  
Korea

The following sample(s) was/were submitted and identified by/on behalf of the client as:-

**SGS File No.** : AYS18-03726  
**Sample Description** : ONE SAMPLE OF PRINTABLE PU  
**Color** : N/A  
**Style no./Item no.** : COL-01, COL-03, COL-07  
**Order No.** : N/A  
**Country of Origin** : N/A  
**Country of Destination** : N/A  
**Proposed care Instruction** : USING WASHING MACHINE (WATER TEMPERATURE 40 °C, USING DETERGENT WITHOUT SOFTENER) DO NOT IRONING, DO NOT DRY CLEANING, SHADE LINE DRY  
**Received Date** : 2018. 02. 28  
**Test Period** : 2018. 02. 28 TO 2018. 03. 12  
**Purpose of Test Report** : For Self Reference.  
**Test Method** : Please refer to next page(s).  
**Test Results** : Please refer to next page(s).  
**Result summary** : Selected test(s) as requested by client

SGS Korea Co., Ltd.

Daesung Lee / Technical Manager

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at [www.sgs.com/terms\\_e-document.htm](http://www.sgs.com/terms_e-document.htm). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s).

## Test Conducted

## Results

### Appearance after 5<sup>th</sup> Washing (Print part only)

Test Method: Washing Procedure: AATCC 150-2012: Machine wash at (44 ± 4.2) °C with 1.8 kg dummy loading, Normal cycle, Line dry at 25 °C, Add 66.0 g of 1993 AATCC Standard Reference Detergent

- Observation on washed sample

The color of the sample was almost the same as that of the original state. (grade 4.5)

No noticeable change was found.

The self-staining of the sample was grade 5.

Therefore, the general appearance of the washed sample is **satisfactory**.

### Appearance after 10<sup>th</sup> Washing (Print part only)

Test Method: Washing Procedure: AATCC 150-2012: Machine wash at (44 ± 4.2) °C with 1.8 kg dummy loading, Normal cycle, Line dry at 25 °C, Add 66.0 g of 1993 AATCC Standard Reference Detergent

- Observation on washed sample

The color of the sample was almost the same as that of the original state. (grade 4.5)

No noticeable change was found.

The self-staining of the sample was grade 5.

Therefore, the general appearance of the washed sample is **satisfactory**.

### Appearance after 15<sup>th</sup> Washing (Print part only)

Test Method: Washing Procedure: AATCC 150-2012: Machine wash at (44 ± 4.2) °C with 1.8 kg dummy loading, Normal cycle, Line dry at 25 °C, Add 66.0 g of 1993 AATCC Standard Reference Detergent

- Observation on washed sample

The color of the sample was almost the same as that of the original state. (grade 4.5)

No noticeable change was found.

The self-staining of the sample was grade 5.

Therefore, the general appearance of the washed sample is **satisfactory**.

<Note> Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.

<Note> The test was conducted by applicant's request.

**Picture of Sample as Received :**



**AYSA18-03726**

\*\*\* End of Report \*\*\*

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at [www.sgs.com/terms\\_e-document.htm](http://www.sgs.com/terms_e-document.htm). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s).